


PRODUCT DATASHEET

Confidex Ironside Micro™ NFC



Ruggedized NFC Tag for harsh use cases including impacts, chemicals and moisture.

ELECTRICAL SPECIFICATION

Device type

NTAG213: NFC Forum Type 2

SLIX2: NFC Forum Type 5

Air interface protocol

NTAG213: ISO 14443A

SLIX2: ISO 15693

Operational frequency

13,56 MHz

IC type

NXP NTAG213

NXP ICODE SLIX2

Memory configuration

With NTAG213: User memory 144 bytes

With SLIX2: User memory 2528 bits

Read range*

With NTAG213:

Mobile phone up to 3cm

Fixed reader up to 7cm

With SLIX2:

Mobile phone up to 3cm

Fixed reader up to 29cm

Applicable surface materials*

Works on any material, also on metal

* Read ranges are measured in laboratory environment and there can be some variation in real application. Also used surface material might affect the read range.

MECHANICAL SPECIFICATION

Tag materials

High quality engineering plastics

Weight

4,3 g

Delivery format

Single, 500pcs in box

Dimensions

27 x 27 x 5,5 mm / 1.06 x 1.06 x 0.22 in

ENVIRONMENTAL RESISTANCE

Operating temperature

-35°C to +85°C / -31°F to +185°F

Ambient temperature

-35°C to +85°C / -31°F to +185°F

IP classification

IP68

Chemical resistance

No physical or performance changes in

- 168h Motor oil exposure
- 168h Salt water (salinity 10%) exposure
- 5h Sulfuric acid (10%, pH 2) exposure
- 1h NaOH (10%, pH 13) exposure

Contact with acetone should be avoided.

Expected lifetime

Years in normal operating conditions

Values in the table are the best recommendations; resistance against environmental conditions depends on the combination of all influencing factors, exposure duration and chemical concentrations. Thus, product's final suitability for certain environmental conditions is recommended to be tested. Contact Confidex for more specific information.

PERSONALIZATION OPTIONS

Pre-encoding

- Customer-specific encoding.

Customized data label

- Customer-specific layout including logo, text, numbers, barcodes etc.

Customized laser engraving

- Customer-specific layout including logo, text, numbers, barcodes etc.

INSTALLATION INSTRUCTIONS

Confidex Ironside Micro™ can be attached with several fixing methods:

1. 3M 300LSE high performance acrylic adhesive (not included by default)

When background adhesive is ordered the tag is delivered with adhesive attached. When mounting the tag with its adhesive background, clean and dry the surface for obtaining the maximum bond strength. Ideal application temperature is from +21°C to +38°C (+70°F to +100°F), bond strength can be improved with firm application pressure and moderate heating from +38°C to +54°C (+100°F to +130°F). Installation at temperatures below 10°C (50°F) is not recommended.

2. Other adhesive fixings
 - Polyurethane adhesives
 - Epoxies
 - Silicone sealants

Silicone sealants like Dow Corning AS 7096 provide very high bond strength and resistance against mechanical stress. When tag is attached with sealant adhesive, insert a layer of sealant under the tag and press the tag on the surface. Increase the bond by adding extra sealant from the tag holes. Please refer to silicone sealant supplier for exact fixing instructions.

3. Mechanical fixing
 - Screws (size M3)
 - Pop rivets
 - Plastic rivets (size 3mm)

Mechanical fixing is recommended to be used in every application that includes risk for high mechanical stress or low temperature during tag fixing. During fixing make sure there is no air gap left in between the metal surface and tag.

ORDER INFORMATION

Product number: 3001300
Product name: Confidex Ironside Micro™ NFC NTAG213

Product number: 3002976
Product name: Confidex Ironside Micro™ NFC SLIX2

For other versions, additional information and technical support contact Confidex Ltd.

DISCLAIMER

THE MATERIALS, PRODUCTS AND SERVICES ARE SOLD SUBJECT TO ITS STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, CONFIDEX MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBE HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN CONFIDEX STANDARD CONDITIONS OF SALE, CONFIDEX AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.

Each user bears full responsibility for making its own determination as to the suitability of Confidex products, materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished systems incorporating Confidex products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Confidex.